



Technical Data Sheet

Arcophane CLR Q1 / Q2

Clear dissymmetrical release polyester film

Base(s)	Kolon Astroll® CD971, Toray Lumirror® 60.01...
----------------	--

Technical data

Properties	Method	Unit	23 µm	36 µm
General				
Total thickness	Internal	µm	23	36
Relative density (23°)	ASTM D.1505	g/cm ³	1.395	
Melting point	-	°C	260	
Mechanical				
Tensile strength at break	ASTM D.882	daN/mm ²	25	22
Elongation at break	ASTM D.882	%	140	150
Thermal				
Shrinkage MD 150°C-30mn	ASTM D.1204	%	<2.5	
Shrinkage TD 150°C-30mn	ASTM D.1204	%	<0.4	
Specific				
Peeling strength (Q1)	Internal	N/2.5cm	0.15	
Peeling strength (Q2)	Internal	N/2.5cm	0.11	

MD: Machine direction
 TD: Transversal direction

All typical values of properties relate to assessment made at time of manufacture.
 This specification is confidential and submitted to the other party for mutual agreement.

v3.0 created: 01/05/2002 modified: 30/01/2012