



Technical Data Sheet

Arcophane SRDT

Clear polyester film

Base(s)	Clear bases
----------------	-------------

Technical data

Properties	Method	Unit	50 µm	175 µm
General				
Total thickness	Internal	µm	50	175
Relative density (23°)	ASTM D.1505	g/cm ³	1.395	
Melting point	-	°C	260	
Mechanical				
Tensile strength at break	ASTM D.882	daN/mm ²	12	18
Elongation at break	ASTM D.882	%	180	220
Thermal				
Shrinkage MD 150°C-30mn	ASTM D.1204	%	<2.5	
Shrinkage TD 150°C-30mn	ASTM D.1204	%	<0.5	
Specific				
Surface tension	ASTM D.2578	dynes/cm	50	
Friction coefficient	ASTM D.1894	µs	0.30	

All typical values of properties relate to assessment made at time of manufacture.
 This specification is confidential and submitted to the other party for mutual agreement.

v3.0 created: 01/05/2002 modified: 30/01/2012