



Technical Data Sheet

Stabiphane MTWIJ

Double matt inkjet polyester film

Base(s)	Clear bases
----------------	-------------

Technical data

Properties	Method	Unit	50 µm	75 µm	100 µm
General					
Total thickness	Internal	µm	70	95	120
Relative density (23°)	ASTM D.1505	g/cm ³	1.395		
Melting point	-	°C	260		
Mechanical					
Tensile strength at break	ASTM D.882	daN/mm ²	18		
Elongation at break	ASTM D.882	%	140		
Thermal					
Shrinkage MD 150°C-30mn	ASTM D.1204	%	<0.9		
Shrinkage TD 150°C-30mn	ASTM D.1204	%	<0.6		
Specific					
Smoothness	TAPPI T.479	s	<30		
Opacity UV	Internal	%	60		
Withness	Internal	%	>79		

MD: Machine direction
 TD: Transversal direction

All typical values of properties relate to assessment made at time of manufacture.
 This specification is confidential and submitted to the other party for mutual agreement.

v3.0 created: 01/05/2002 modified: 30/01/2012